



# **Reliability Test Report**

Product Name: CA-IS206X & CA-IS209X

Report Version: V1.1



# **Contents**

1.	Overv	/iew	3
2.	Part I	Number List	3
3.	Produ	uct Information	3
	3.1.	Wafer Information	3
	3.2.	Package Information	3
4.	Relial	oility Qualification Plan	4
	4.1.	Device Qualification Test Requirements	4
	4.2.	Nonhermetic Package Qualification Test Requirements	4
5.	Relial	oility Test Results	5
	5.1.	Device Reliability Test Results	5
	5.2.	Package Reliability Test Results	5
6	Concl	usion	5



#### 1. Overview

Reliability testing of microelectronic products is a risk mitigation process designed to ensure the service life of device in customer applications. Semiconductor wafer manufacturing process and package-level reliability can be assessed in a variety of ways and may include accelerated environmental test conditions. Chipanalog evaluates manufacturability of the device to verify a robust silicon and assembly flow to ensure continuity of supply to customers. Chipanalog qualifies new devices, significant changes, and product families based on JEDEC JESD47. CA-IS206X & CA-IS209X series chips are packaged with the same wafer. The differences between part numbers are the package and bonding diagram. The data shown is representative of the material sets, processes, and manufacturing sites used by the device family.

### 2. Part Number List

Package Type	Part Number
COLC1C M/D/M/	CA-IS2092W/CA-IS2092VW
SOIC16-WB(W)	CA-IS2062W/CA-IS2062VW

**Note:** JEDEC specification is designed to also qualify a family of similar components utilizing the same fabrication process, design rules, and similar circuits. The family qualification may also be applied to a package family where the construction is the same and only the size and number of leads differs.

#### 3. Product Information

#### 3.1. Wafer Information

Wafer ID	SHENGFO	EUROPA
Die Tech	BCDXXX	BCDXXX

## 3.2. Package Information

Assembly site	UNIMOS
FT site	UNIMOS
Package	SOIC16-WB(W)
Lead frame	Cu
Bond wire	25um AuPdCu
MSL level	MSL3



## 4. Reliability Qualification Plan

## 4.1. Device Qualification Test Requirements

Stress	Ref.	Abbv.	Conditions	Duration /Accept
Electrical Parameter	JESD86	ED	Per Datasheet	Per Datasheet
Assessment	JE3D00	ED	Per Datastieet	Per Datasneet
High Temperature JESD22-A108,		HTOL	T <sub>J</sub> ≥ 125°C	1000 hrs/0 Fail
Operating Life	JESD85	V <sub>CC</sub> ≥V <sub>CC</sub> max		
Human Body Model	IC 001	ESD-	T <sub>A</sub> = 25°C	Classification
ESD	JS-001	HBM	1A = 25 C	Classification
Charged Device	IC 002	ESD-	T 25°C	Classification
Model ESD	JS-002	CDM	T <sub>A</sub> = 25°C	Classification
Latch-Up	JESD78	LU	Class I or Class II	0 Fail

## 4.2. Nonhermetic Package Qualification Test Requirements

Stress	Ref.	Abbv.	Conditions	Duration /Accept
MSL Preconditioning	JESD22-A113	PC	Per appropriate MSL level per J-STD-020	Electrical Test (optional)
High Temperature Storage	JESD22-A103 & A113	HTSL	150°C, 1000 hrs	1000 hrs/0 Fail
Temperature Humidity Bias	JESD22-A101	ТНВ	85°C, 85% RH, V <sub>CC</sub> max	1000 hrs/0 Fail
Highly Accelerated Temperature and Humidity Stress	JESD22-A110	HAST	130°C/110°C, 85% RH, V <sub>CC</sub> max , 33.3psia/17.7 psia	96/264 hrs/0 Fail
Temperature Cycling	JESD22-A104	TC	-65°C to +150°C	500 cycles/0 Fail
Unbiased Temperature/Humidity	JESD22-A102	AC	121°C/100% RH, 29.7 psia	96 hrs/0 Fail
Bond Pull Strength	M2011	BPS	Characterization, Pre Encapsulation	Ppk≥1.66 or Cpk≥1.33
Bond Shear	JESD22-B116	BS	Characterization, Pre Encapsulation	Ppk≥1.66 or Cpk≥1.33
Solderability	M2003 JESD22-B102	SD	Characterization	0 Fail

**Note**: Either HAST or THB may be chosen.



## 5. Reliability Test Results

## **5.1. Device Reliability Test Results**

Stress	Condition	Duration	Sample Size	Result	Classification
ED	Per Datasheet	/	10*3 lots	Pass	/
HTOL	T <sub>A</sub> = 125°C, V <sub>CC</sub> = 5.5V	1000 hrs	77*3 lots	Pass	/
ESD-HBM	T <sub>A</sub> = 25°C	/	3*1 lot	Pass	Class 3A
ESD-CDM	T <sub>A</sub> = 25°C	/	3*1 lot	Pass	Class C3
LU	T <sub>A</sub> = 25°C	/	3*1 lot	Pass	Class I A

## 5.2. Package Reliability Test Results

Package Type: SOIC16-WB(W)					
Stress	Condition	Duration	Sample size	Result	
PC	MSL 3	/	231*3 lots	Pass	
HTSL	T <sub>A</sub> = 150°C	1000 hrs	77*3 lots	Pass	
HAST	130°C/85% RH, Vcc=5.5V, 33.3psia	96 hrs	77*3 lots	Pass	
TC	-65°C to +150°C	500 cycles	77*3 lots	Pass	
AC	121°C/100% RH, 29.7psia	96 hrs	77*3 lots	Pass	
BPS	M2011	/	30 bonds/5 ea.	Pass	
BS	JESD22-B116	/	30 bonds/5 ea.	Pass	
SD	Steam aging 8hrs, 245°C dipping	/	22 leads*1 lot	Pass	

## 6. Conclusion

CA-IS206X & CA-IS209X series products are qualified with JEDEC standards.



#### **Disclaimer**

This information is provided to assist customers in design and development. It could change for technology innovation without notice.

The devices are shipped after passing final test. Customers are responsible to conduct sufficient engineering and additional qualification testing to determine whether a device is suitable for use in their applications.

License to customers to use the information is limited to the development of applications using the device. Apart from above, the information shall not be reproduced or displayed, and Chipanalog shall not be liable for any claims, compensation, costs, losses or liabilities arising out of the use of the information.

#### **Trademarks**

Chipanalog Inc.® 、Chipanalog® are trademarks of Chipanalog.

### **Revision History**

Revision	Change Log	Date
V1.0	Initial release	Sep, 2022
V1.1	Release EN version;	May 2024
V 1.1	Add qualification lots	May, 2024